

Vinyl CarpentryTM Value Soffit

Vinyl Soffit

General Description: Value vinyl soffit is appropriate for use in new construction for single family homes, multi-housing projects, and light commercial developments. Value is also an ideal product for remodeling. The vented styles are for eaves installation only. The solid styles are appropriate for porch ceiling installation.

Styles:

Profile	Finish	Net Free Air Space Per Sq. Ft.	Panel Projection	Wall Thickness (Nominal)	Lock Design	Colors	Accessory Pocket
Triple 4" Solid	Matte	—	1/2"	.036"	Post-formed	9	1/2" or 3/4"
Triple 4" Fully Vented	Matte	5.9 Sq. In.	1/2"	.036"	Post-formed	9	1/2" or 3/4"
Triple 4" Center Vented	Matte	2.0 Sq. In.	1/2"	.036"	Post-formed	1	1/2" or 3/4"
D5" Solid	Matte	—	1/2"	.038"	Post-formed	9	1/2" or 3/4"
D5" Fully Vented	Matte	6.4 Sq. In.	1/2"	.038"	Post-formed	9	1/2" or 3/4"

Colors:

Colonial White	Light Maple	Savannah Wicker	Heritage Cream	Snow
Desert Tan	Natural Clay	Sterling Gray	Herringbone	

Triple 4" Center Vented available in Colonial White and Snow only.

Lock: Designed for ease of installation, Value panels feature a post-formed lock popular with installers for its locking assurance and trouble-free handling.

Accessories: CertainTeed manufactures a wide range of accessories which are compatible with Value soffit. Accessory products include installation components, receiving channels and decorative moldings.

Composition: Value soffit is produced using CertaVinTM custom-formulated PVC resin. This resin is produced exclusively by CertainTeed allowing CertainTeed to maintain the high quality of its siding products. CertainTeed's Value soffit is in compliance with the ASTM Specification for Rigid Polyvinyl Chloride (PVC) siding D 3679 and D 4477.

Technical Data: Value soffit meets the weathering standard in ASTM D 3679 using ASTM D 1435 procedure. As shown in Table 1, Value soffit is in compliance with ASTM Fire and Smoke procedures and meets or exceeds International Building Code requirements.

Table 1

ASTM E 84	Flame Spread Index 20 Fuel Contribution 0 Smoke Development Index 390
ASTM D 1929	Self-ignition temperature 813°F
ASTM D 635	Material is self-extinguishing with no measurable extent of burn when tested in accordance with this specification.
NFPA 268	Radiant Heat Test - Ignition Resistance of Exterior Walls - Conclusion that CertainTeed met the conditions for allowable use as specified in section 1406 of the International Building Code.

Important Fire Safety Information: When rigid vinyl siding is exposed to significant heat or flame, the vinyl will soften, sag, melt or burn, and may thereby expose material underneath. Care must be exercised when selecting underlayment materials because many underlayment materials are made from organic materials that are combustible. You should ascertain the fire properties of underlayment materials prior to installation. All materials should be installed in accordance with local, state, and federal building code and fire regulations.

Documents: CertainTeed Vinyl Siding meets the requirements of one or more of the following specifications.

Texas Department of Insurance Product Evaluation EC-11

New York City Approval MEA #285-93M, 284-93-M

Conforms to ASTM Specification D4477

ICC-ES Evaluation Report ESR-1066

For specific product evaluation/approval information, call 800-233-8990.

Conforms to UBC Standard 14-2

Conforms to ASTM Specification D3679

Florida BCIS Approval FL1573, FL10421

CCMC #13008-L

Installation: Prior to commencing work, verify governing dimensions of building, examine, clean and repair, if necessary, any adjoining work on which the siding is in any way dependent for its proper installation. Sheathing materials must have an acceptable working surface. Siding, soffit and accessories shall be installed in accordance with the latest editions of CertainTeed installation manuals on siding and soffit. Installation manuals are available from CertainTeed and its distributors.

Warranty: CertainTeed supports Value soffit products with a Lifetime Limited Warranty. The warranty is transferable if the home is sold.

Technical Services: CertainTeed maintains an Architectural Services staff to assist building professionals with questions regarding CertainTeed siding products. Call 800-233-8990 for samples and answers to technical or installation questions.

Sample Short Form Specification: Soffit as shown on drawings or specified herein shall be Value vinyl soffit as manufactured by CertainTeed Corporation, Valley Forge, PA. The soffit shall have a .036" nominal thickness (T4") or .038" nominal thickness (D5"). Installation shall be in accordance with manufacturers instructions.

Three-part Format Specifications: Long form specifications in three-part format are available from CertainTeed by calling our Architectural Services Staff at 800-233-8990. These specifications are also available on our website at certainteed.com.



CertainTeed Corporation
P.O. Box 860
Valley Forge, PA 19482
certainteed.com
© 4/09