

CertainTeed

ProRoc[®]
BRAND

Wall & Ceiling Spray Textures

Data and Submittal Sheet

DESCRIPTION

ProRoc[®] Wall and Ceiling Spray Textures provide a decorative appearance over gypsum panels and most other interior wall and ceiling surfaces. They are formulated to provide for a variety of decorative options including splatter, knockdown and orange peel designs.

- PROROC[®] MEDIUM-TEX POWDER
- PROROC[®] COARSE-TEX POWDER
- PROROC[®] HIGH HIDING TEX POWDER
- PROROC[®] SPANISH TEX POWDER
- PROROC[®] REINFORCED LITE TEX R/M
- PROROC[®] SPRAY-LITE TEX R/M

SUBMITTAL APPROVAL STAMPS/SIGNATURES

Please check the appropriate products above which are being submitted for approval

Date:

Project:

PRODUCT DATA

MATERIAL: Powder or Ready-Mixed

COLOUR: Off white

PACKAGING: Powder 15 kg - 25 kg (33 lbs - 55 lbs) bags
Ready-Mix 17 L (4.5 US GAL) cartons

COVERAGE: The coverage of ProRoc[®] Wall and Ceiling Textures varies greatly depending on formula base, type of pattern, the condition of the substrate, and the application technique. Please contact your local CertainTeed sales representative for further information.

SHELF LIFE: Ready-Mix 12 months from production code date, when stored properly.
Powders 24 months from production code date, when stored properly.

DRYING TIME: 24 hours in normal conditions.

STORAGE: ProRoc[®] Wall and Ceiling Textures should be stored in a dry, temperate location where there can be no contact with moisture. Rotate stock. Opened bags should be closed tightly before storage. Protect Ready-Mixed textures from freezing.

TECHNICAL REFERENCES:

For additional information on the application of ProRoc[®] Brand products please consult:

- ASTM C 475: Standard Specification for Joint Compound and Joint Tape for Finishing Gypsum Board.
- ASTM C 840: Standard Specification for Application and Finishing of Gypsum Board.
- GA-214: Gypsum Association publication "Levels of Gypsum Board Finish."
- GA-216: Gypsum Association publication "Recommended Specifications for the Application and Finishing of Gypsum Board."

WORKING WITH THE PRODUCT

SITE CONDITIONS:

The room temperature and wallboard should be maintained at 13°C (55°F) for 48 hours prior to application and continuously thereafter until completely dry. Continuous ventilation must be provided to ensure proper drying. When using temporary heating, care should be taken to avoid overheating and high humidity conditions.

SURFACE PREPARATION:

Ensure that surfaces to be decorated are thoroughly dry and free of dirt, oils, mildew and other contaminants.

PRIMING:

All surfaces to be textured should be primed with texture primer prior to application to ensure uniform porosity and texture. Primer should be dry prior to applying texture. Adhere to all manufacturers' specific directions for painting and decorating materials.

MIXING (POWDER)

Use a clean vessel equipped with powder agitator. For initial mix, stir powder into recommended amount of water, agitating during powder addition. Allow to soak for at least 15 minutes — longer in cold water. Remix until a creamy, lump-free mix is obtained. Adjust to spray consistency by adding small amounts of water, if necessary. Over thinning can create an undesirable finish or "soft wall" or chalky condition. Over dilution can also entrain excessive air and foam. Note that the air and mix temperature will affect viscosity.

CertainTeed 

Wall and Ceiling Spray Textures

Data and Submittal Sheet

MIXING (READY MIX)

Prethinning may be necessary; the amount of water added will determine the type of texture achieved.

APPLICATION:

Texture should not be applied until the primer coat is thoroughly dry. Products are specifically designed for hand and spray applications. The desired pattern can be achieved by varying the viscosity of the mix, the orifice opening at the spray tip, or the air supply pressure.

DECORATING:

This product can be painted after drying. Adhere to all manufacturers' specific directions for painting and decorating materials.

LIMITATIONS:

- Application below grade or in high-humidity areas is not recommended.
- May contribute to sagging of gypsum board ceilings in humid conditions. The potential for sagging can be minimized by taking the following precautions:
- Use ProRoc[®] Interior Ceiling board or gypsum board applied perpendicular to the framing at the proper spacing recommendation for the board thickness (see GA-216, Tables 1 and 4.)
- Excessive amounts of insulation should not be added without additional support (GA-216, Table 2). Where the gypsum board supports ceiling insulation and is finished with a water-based texture material, either spray or hand applied, only 15.9 mm (5/8") gypsum board, or 12.7 mm (1/2") gypsum ceiling board, application perpendicular to the framing members shall be used.
- The relative humidity should be controlled by providing adequate ventilation before, during and after gypsum board and finish application.
- Temperatures should be maintained between 13°C and 21°C (55°F and 70°F).
- Gypsum board should be thoroughly dry and at ambient temperature before application.
- Joint treatment should be thoroughly dry before applying any decoration.

- Individual coats of primer and paint shall be dry before the application of successive coats.
- Texture is not washable unless painted.

MSDS:

MSDS Material Safety Data Sheets are available on our web site, www.CertainTeed.com.

WARNING:

Dust generated from sanding product may cause eye, skin, nose, throat or respiratory irritation. Use wet-sanding to avoid creating dust. Avoid inhalation of dust and eye contact. Product contains silica. Inhalation of respirable silica dust can cause silicosis, a potentially disabling lung disease, and is known to the State of California to cause lung cancer.

When sanding, drilling or abrading product during installation or handling: (1) Ensure adequate ventilation. (2) Wear a dust mask or, if dust may exceed PEL, use NIOSH/MSHA approved respirator. (3) Warn others in area. (4) Wear eye protection.

If eye contact occurs, flush thoroughly with water for 15 minutes. For further information, refer to Material Safety Data Sheet or consult manufacturer by calling 1-866-427-2872.

KEEP OUT OF REACH OF CHILDREN.

WARRANTY:

Since methods and condition of application such as temperature, humidity and over thinning are beyond our control, CertainTeed Gypsum (CertainTeed) will not be responsible for the failure of this product when not used according to directions and specifications and accepted standards of procedure inherent in drywall application; or when reasonable allowance is not made by the user for adverse weather and job conditions. However, if this product proves to be defective, maximum liability shall be limited to replacement of the material only or refund of the purchase price. This shall be the full limit whatsoever of CertainTeed's liability. All claims shall be submitted in writing to CertainTeed within thirty days from the date of discovery. State or Federal laws may provide rights in addition to this warranty that cannot be modified or excluded.

CertainTeed Corporation
P.O. Box 860
Valley Forge, PA 19482

Professional: 800-233-8990
Consumer: 800-782-8777
www.certainteed.com

CertainTeed 

Characteristics, properties or performance of materials or systems manufactured by CertainTeed herein described are derived from data obtained under controlled test conditions. CertainTeed makes no warranties, express or implied, as to their characteristics, properties or performance under any variations from such conditions in actual construction. CertainTeed assumes no responsibility for the effects of structural movement.

™@ CertainTeed and the tag line "Quality made certain. Satisfaction guaranteed." are trademarks of CertainTeed Corporation. All other trademarks are the property of BPB Inc. or its affiliates and related companies.

NOTICE: The information in this document is subject to change without notice. CertainTeed assumes no responsibility for any errors that may inadvertently appear in this document.

©2008 CertainTeed Corporation. Printed in Canada on recycled paper. ♻ February 2008 Form #: L-SD-003-E