



Evaluation Listing CCMC 13095-L GlasRoc[®] Sheathing and GlasRoc[®] Sheathing Type X

Evaluation Issued:	2004-04-21
Re-evaluated:	2013-03-04
Re-evaluation due:	2016-04-21

Preface: Masterformat 06 16 43.01, Glass Mat Gypsum Board

Preface Issued:	2007-07-17
------------------------	------------

Scope

The Evaluation Listings in this Section apply to glass mat gypsum board to be used as an exterior wall sheathing for a weather barrier.

The proponent has demonstrated that the product meets the requirements of ASTM C 1177-04e1, "Glass Mat Gypsum Substrate for Use as Sheathing."

Product conforming to this Standard consist of a noncombustible water-resistant core made from gypsum and surfaced with glass mat partially or completely embedded in the core.

Standard

Table 1. Physical and Performance Requirements for Glass Mat Gypsum Board

Property		Unit	Requirement	
			12.7 mm thick	15.9 mm thick
Flexural strength	bearing edges perpendicular to the substrate edge	N	≥ 445	≥ 623
	bearing edges parallel to the substrate edge		≥ 356	≥ 445
Humidified deflection		mm	≤ 6	≤ 3
Core, end and edge hardness		N	≥ 67	≥ 67
Nail pull resistance		N	≥ 356	≥ 400
Water resistance		n/a	≤ 10 weight % after 2-h immersion	≤ 10 weight % after 2-h immersion

Table 1. Physical and Performance Requirements for Glass Mat Gypsum Board (cont.)

Property		Unit	Requirement	
			12.7 mm thick	15.9 mm thick
Dimensions and tolerances	thickness	mm	12.7 ± 0.8 nominal thickness with local variations of ± 1.6	15.9 ± 0.8 nominal thickness with local variations of ± 1.6
	width	mm	up to 1 220 ± 3	up to 1 220 ± 3
	length	mm	1 840 ± 6 to 3 660 ± 6	1 840 ± 6 to 3 660 ± 6
	end squareness	n/a	Square ± 3 mm in the full width of the substrate	Square ± 3 mm in the full width of the substrate
	edges and ends	n/a	Straight and either square, beveled, featured, tapered, or featured and tapered	Straight and either square, beveled, featured, tapered, or featured and tapered
Finish and appearance		n/a	Free of any cracks or imperfections that would render it unfit for its designed use	Free of any cracks or imperfections that would render it unfit for its designed use

Labelling

Each gypsum panel product or package shall have legibly marked thereon the following:

- thickness;
- name of the producer or supplier;
- brand name, if any; and
- the ASTM specification for the product.

National Building Code of Canada (NBC)

NBC References

ASTM C 1177/C 1177M-04e1 is referenced in:

- a. NBC 2005, Division B, Table 5.10.1.1.;
- b. NBC 2005, Division B, Table 9.23.16.2.A, for 12.7-mm-thick or greater; and
- c. NBC 2005, Division B, Article 9.23.16.3 Gypsum sheathing shall not be used for the attachment for cladding materials

Evaluation Listing CCMC 13095-L: GlasRoc[®] Sheathing and GlasRoc[®] Sheathing Type X

Evaluation Issued: 2004-04-21
Re-evaluated: 2013-03-04
Re-evaluation due: 2016-04-21

1. Evaluation

Conforms to ASTM C 1177/C 1177M-08 for 12.7-mm- and 15.9-mm-thick boards.

2. Description

The products are made from a reinforcing glass mat, which is fully embedded in a water-resistant gypsum core positioned beneath a paperless polymer-modified gypsum surface with a protective acrylic coating on the exterior face.

3. Standard and Regulatory Information

See the [Preface](#) and the standard for explanation.

Listing Holder

CertainTeed Gypsum Canada, Inc.
2424 Lakeshore Road West
Mississauga, ON L5J 1K4

Telephone: 905-823-9881

Fax: 905-823-4464

Plant(s)

Cody, WY, U.S.A.

Disclaimer

This Listing is issued by the Canadian Construction Materials Centre, a program of NRC Construction at the National Research Council of Canada. The Listing must be read in the context of the entire CCMC Registry of Product Evaluations.

Readers must confirm that the Listing is current and has not been withdrawn or superseded by a later issue. Please refer to http://www.nrc-cnrc.gc.ca/eng/solutions/advisory/ccmc_index.html, or contact the Canadian Construction Materials Centre, NRC Construction, National Research Council of Canada, 1200 Montreal Road, Ottawa, Ontario, K1A 0R6. Telephone (613) 993-6189. Fax (613) 952-0268.

NRC has evaluated the material, product, system or service described herein only for those characteristics stated herein. The information and opinions in this Listing are directed to those who have the appropriate degree of experience to use and apply its contents. This Listing is provided without representation, warranty, or guarantee of any kind, expressed, or implied, and the National Research Council of Canada (NRC) provides no endorsement for any evaluated material, product, system or service described herein. NRC accepts no responsibility whatsoever arising in any way from any and all use and reliance on the information contained in this Listing. NRC is not undertaking to render professional or other services on behalf of any person or entity nor to perform any duty owed by any person or entity to another person or entity.

Date modified:
2013-03-25