


FLINTBOARD® ISO COLD

Polyisocyanurate Roof Insulation

Product Information



Rigid board insulation specifically for roofing membranes applied using *cold adhesive.

*Not for use with hot applied roofing materials.

FlintBoard® ISO Cold Polyisocyanurate Roof Insulation features a closed-cell polyiso core with integrally-laminated, heavy-coated glass facers. FlintBoard ISO Cold has been specifically engineered with a more durable facer and higher dimensional stability. Typically specified for hot asphalt, BUR, modified bitumen, and single-ply membrane systems.

FlintBoard ISO Cold is offered in a variety of thicknesses, providing long-term thermal resistance (LTTR) values from 6.0 to 25.0. FlintBoard ISO Cold is also available in 25-psi formula. Available in 4' x 4' (1220 mm x 1220 mm) and 4' x 8' (1220 mm x 2440 mm) panels.

FlintBoard ISO Cold is the recommended roof insulation for use in conjunction with CertainTeed Cold Applied Commercial Roofing Systems including Flintlastic® Roof Systems which utilize SBS modified bitumen adhesive as the membrane bonding agent.

Typical Physical Properties

PROPERTY	TEST METHOD	TYPICAL RESULTS
Dimensional Stability (Length and Width)	ASTM D2126	< 2%
Compressive Strength (10% Deformation)	ASTM D1621	20 psi (140 kPa) or 25 psi (172 kPa)
Water Absorption	ASTM C209 ASTM D2842	< 1% < 3.5%
Moisture Vapor Transmission	ASTM E96	< 1.0 perm (85.0ng/ (Pa•s•m ²))
Product Density	ASTM D1622	Nominal 2.0 pcf (32.04 kg/m ³)
Flame Spread	ASTM E84 (Full 10 min.Test)	40-60*
Tensile Strength	ASTM D1623	> 730 psf (35 kPa)
Service Temperature	—	-40 to 200°F

The physical properties listed above are presented as typical average values as determined by accepted ASTM test methods and are subject to normal manufacturing variation. This data is offered as a service to our customers and is subject to change. All information can be confirmed by contacting CertainTeed's Technical Department.

*The numerical ratings as determined by ASTM Test Method E84 are not intended to reflect hazards presented by this or any other material under actual fire conditions. A flame spread index of 75 or less meets code requirements regarding flame spread for foam plastic roof insulation. However, flame spread values are not required for foam plastic insulation used in roof deck constructions that comply as an assembly with FM 4450 or UL 1256.

Installation

Refer to the CertainTeed FlintBoard product brochure and to the CertainTeed Commercial Roof Systems Manual for installation details regarding FlintBoard Roof Insulation. Refer also to Technical Bulletin CT-ISO-08-02.

Storage

Storage/Precautions: Factory-applied packaging is intended only for protection during transit. When stored outdoors or on the job site, packages should be stacked on pallets at least three inches above ground level and completely covered with a weatherproof covering such as a tarpaulin. The temporary factory-applied packaging should be slit or removed to prevent accumulation of condensation. Roof insulation that has become wet or damaged should be removed and replaced with solid, dry insulation.

FlintBoard ISO Cold Thicknesses and LTTR

Thickness		LTTR Value*	Metal Deck Flute Spanability	
IN	MM		IN	MM
1.0	25.40	5.7	2.625	66.675
1.5	38.10	8.6	4.375	111.125
1.8	45.72	10.3	4.375	111.125
2.0	50.80	11.4	4.375	111.125
2.5	63.50	14.4	4.375	111.125
2.6	66.04	15.0	4.375	111.125
3.0	76.20	17.4	4.375	111.125
3.1	78.74	18.0	4.375	111.125
3.3	83.82	19.2	4.375	111.125
3.5	88.90	20.5	4.375	111.125
3.8	96.52	22.3	4.375	111.125
4.0	101.60	23.6	4.375	111.125
4.3	109.22	25.5	4.375	111.125
4.5	114.30	26.8	4.375	111.125

*LTTR (Long-term thermal resistance) values are based on ASTM C 1289, effective 1/1/2014, which provides updated 15 year time weighted averages.

Warning! Do Not Leave Exposed: This product is a polyiso organic plastic foam and will burn if exposed to an ignition source of sufficient heat and intensity, or open flame, such as a welder’s torch. Like other organic materials, this product will release smoke if ignited. Do not apply flame directly to FlintBoard roof insulations. This product should be used only in strict accordance with CertainTeed recommended uses and instructions.

FlintBoard ISO Cold Compliances:

- ASTM C1289, Type II, Class 2, Grade 2 (20 psi) or Grade 3 (25 psi)
- Miami-Dade County, Florida
- California State Insulation Quality Standards and Title 25, Foam Flammability Criteria
- IBC, NBC, UBC, SBC Sections on Foam Insulation
- Meets CAN/CGSB-51.26-M86. Meets CAN/ULC-S704.
- State of Florida Product Approval

FM Standard 4450/4470 Approval

FlintBoard ISO Cold is approved for Class 1 insulated steel, wood, concrete and gypsum roof deck construction for both 1-60 and 1-90 Windstorm Classifications. Refer to FM Approvals RoofNav for details on specific systems.

UL Standard 1256 Classification

Insulated metal deck construction assemblies – Construction #120 and Construction #123.

UL Standard 790 (ASTM E108) Classification

Class A with most roof membrane systems. See UL Roofing Materials & Systems Directory.

UL Standard 263 Fire Resistance Classification (ASTM E119)

Some classifications for fire resistance are P225, P230, P259, P508, P510, P514, P701, P710, P713, P717, P718, P719, P720, P722, P723, P724, P725, P727, P728, P729, P730, P732, P801, P814, P815, P818, P819, P823 and P828. See UL Fire Resistance Directory for updated listings.

UL Certified for Canada

UL of Canada

Insulated Roof Deck Assemblies
Construction #C34
Meets CAN/ULC-S126-M86, CAN/ULC-S101-M89,
CAN/ULC-S107-M87 Criteria.

For more information, contact CertainTeed Commercial Roofing Technical Services at 800-396-8134 x2.

ASK ABOUT ALL OF OUR OTHER CERTAINTEED® PRODUCTS AND SYSTEMS:

ROOFING • SIDING • TRIM • DECKING • RAILING • FENCE
GYPSUM • CEILINGS • INSULATION

www.certainteed.com <http://blog.certainteed.com>

CertainTeed Corporation
P.O. Box 860
Valley Forge, PA 19482

Professional: 800-233-8990
Consumer: 800-782-8777

