


## FLINTBOARD® ISO-T COLD

### Tapered Polyisocyanurate Roof Insulation

#### Product Information



**Rigid, board insulation specifically for roof membranes applied using \*cold adhesive in a tapered design to promote proper roof drainage.**

\*Not for use with hot applied roofing materials.

FlintBoard® ISO-T Cold Tapered Polyisocyanurate Roof Insulation is manufactured in a tapered profile to offer the combination of high thermal value plus promotion of proper roof drainage. As with regular FlintBoard ISO Cold, FlintBoard ISO-T Cold features closed-cell polyiso core with integrally laminated heavy, coated glass facers. In multi-layer roof system applications, FlintBoard ISO-T Cold is installed over one layer of FlintBoard ISO in accordance with CertainTeed specifications.

FlintBoard ISO-T Cold is offered in a variety of tapered panels, providing average long-term thermal resistance (LTTR) values from 4.2 to 12.9. Higher LTTR values can be achieved with layers of flat FlintBoard ISO. Available in 4' x 4' (1220 mm x 1220 mm) panels only.

FlintBoard ISO-T Cold is a recommended roof insulation for use in conjunction with CertainTeed Commercial Roofing Systems including Flintlastic® Roof Systems which utilize SBS modified bitumen adhesive as the membrane bonding agent.

#### Typical Physical Properties (Foam Portion)

PROPERTY (Foam Portion)	TEST METHOD	TYPICAL RESULTS
Dimensional Stability (Length and Width)	ASTM D2126	< 2%
Compressive Strength (10% Deformation)	ASTM D1621	20 psi (140 kPa) or 25 psi (172 kPa)
Water Absorption	ASTM C209 ASTM D2842	< 1% < 3.5%
Moisture Vapor Transmission	ASTM E96	< 1.0 perm (85.0ng/ (Pa•s•m <sup>2</sup> ))
Product Density	ASTM D1622	Nominal 2.0 pcf (32.04 kg/m <sup>3</sup> )
Flame Spread	ASTM E84 (Full 10 min. Test)	40-60*
Tensile Strength	ASTM D1623	> 730 psf (35 kPa)
Service Temperature	—	-40 to 200°F

The physical properties listed above are presented as typical average values as determined by accepted ASTM test methods and are subject to normal manufacturing variation. This data is offered as a service to our customers and is subject to change. All information can be confirmed by contacting CertainTeed's Technical Department.

\*The numerical ratings as determined by ASTM Test Method E84 are not intended to reflect hazards presented by this or any other material under actual fire conditions. A flame spread index of 75 or less meets code requirements regarding flame spread for foam plastic roof insulation. However, flame spread values are not required for foam plastic insulation used in roof deck constructions that comply as an assembly with FM 4450 or UL 1256.

#### Installation

Refer to the CertainTeed FlintBoard product brochure and the CertainTeed Commercial Roof Systems Manual for installation details regarding FlintBoard Roof Insulation. Refer also to Technical Bulletin CT-ISO-08-02.

#### Storage

**Storage/Precautions:** Factory-applied packaging is intended only for protection during transit. When stored outdoors or on the job site, packages should be stacked on pallets at least three inches above ground level and completely covered with a weatherproof covering such as a tarpaulin. The temporary factory-applied packaging should be slit or removed to prevent accumulation of condensation. Roof insulation that has become wet or damaged should be removed and replaced with solid, dry insulation.



**Warning!** Do Not Leave Exposed: This product is a polyiso organic plastic foam and will burn if exposed to an ignition source of sufficient heat and intensity, or open flame, such as a welder's torch. Like other organic materials, this product will release smoke if ignited. Do not apply flame directly to FlintBoard roof insulations. This product should be used only in strict accordance with CertainTeed recommended uses and instructions.

**FlintBoard ISO-T Cold Compliances:**

- ASTM C1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi)
- Miami-Dade County, Florida
- California State Insulation Quality Standards and Title 25 Foam Flammability Criteria
- IBC, NBC, UBC and SBC Sections on Foam Insulation
- State of Florida Product Approval

**FM Standard 4450/4470 Approval**

FlintBoard ISO-T Cold is approved for Class 1 insulated steel, wood, concrete and gypsum roof deck construction for both 1-60 and 1-90 Windstorm Classifications (may be mopped or mechanically fastened to concrete roof deck). Refer to FM Approvals RoofNav Guide for details on specific systems.

**UL Standard 1256 Classification**

Insulated metal deck construction assemblies, Construction #120 and #123.

**UL Standard 790 (ASTM E108) Classification**

Class A with most roof membrane systems. See UL Roofing Materials & Systems Directory.

**UL Standard 263 Fire Resistance Classification (ASTM E119)**

Some classifications for fire resistance are P230, P259, P508, P510, P514, P710, P711, P715, P717, P718, P814, P815, P818, and P828. See UL Fire Resistance Directory for updated listings.

**FlintBoard ISO-T Cold Thicknesses and LTTR**

Marking	Thickness		LTTR Value*	Slope	
	IN	MM		per ft	percent
AA	.05-1.0	12-25	4.3	1/8"	1%
A	1.0-1.5	25-38	7.1	1/8"	1%
B	1.5-2.0	38-50	10	1/8"	1%
C	2.0-2.5	50-63	12.9	1/8"	1%
X	.05-1.5	12-38	5.7	1/4"	2%
Y	1.5-2.5	38-63	11.4	1/4"	2%
Q	0.5-2.5	12-63	8.6	1/2"	4%

\*LTTR (Long-term thermal resistance) values are based on ASTM C 1289, effective 1/1/2014, which provides updated 15 year time weighted averages.

For more information, contact CertainTeed Commercial Roofing Technical Services at 800-396-8134 x2.

**ASK ABOUT ALL OF OUR OTHER CERTAINTEED® PRODUCTS AND SYSTEMS:**

ROOFING • SIDING • TRIM • DECKING • RAILING • FENCE  
GYPSUM • CEILINGS • INSULATION

[www.certainteed.com](http://www.certainteed.com) <http://blog.certainteed.com>

CertainTeed Corporation  
P.O. Box 860  
Valley Forge, PA 19482

Professional: 800-233-8990  
Consumer: 800-782-8777

