


## FLINTBOARD® ISO-T

### Tapered Polyisocyanurate Roof Insulation

#### Product Information



#### Typical Physical Properties

**Rigid board insulation for hot asphalt, coal tar BUR, modified bitumen and single ply roofing systems, in a tapered design to promote proper roof drainage.**

FlintBoard® ISO-T Tapered Polyisocyanurate Roof Insulation is manufactured in a tapered profile to offer the combination of high thermal value plus promotion of proper roof drainage.

FlintBoard ISO-T is offered in a variety of thicknesses, providing long-term thermal resistance (LTTR) values from 4.2 to 12.9. Higher LTTR values can be achieved with layers of flat FlintBoard ISO. FlintBoard ISO-T is a closed-cell, polyiso core integrally laminated to heavy, black (non-asphaltic), fiber-reinforced felt facers. FlintBoard ISO-T is also available in 25-psi formula. Available in 4' x 4' (1220mm x 1220mm) panels only.

FlintBoard ISO-T is the recommended roof insulation for use in conjunction with CertainTeed Commercial Roofing Systems including Flintlastic® Roof Systems.

PROPERTY	TEST METHOD	TYPICAL RESULTS
Dimensional Stability (Length and Width)	ASTM D2126	< 2%
Compressive Strength (10% Deformation)	ASTM D1621	20 psi (140 kPa) or 25 psi (172 kPa)
Water Absorption	ASTM C209 ASTM D2842	< 1% < 3.5%
Moisture Vapor Transmission	ASTM E96	< 1.0 perm (85.0ng/ (Pa•s•m <sup>2</sup> ))
Product Density	ASTM D1622	Nominal 2.0 pcf (32.04 kg/m <sup>3</sup> )
Flame Spread	ASTM E84 (Full 10 min.Test)	40-60*
Tensile Strength	ASTM D1623	> 730 psf (35 kPa)
Service Temperature	—	-40 to 200°F

The physical properties listed above are presented as typical average values as determined by accepted ASTM test methods and are subject to normal manufacturing variation. This data is offered as a service to our customers and is subject to change. All information can be confirmed by contacting CertainTeed's Technical Department.

\*The numerical ratings as determined by ASTM Test Method E84 are not intended to reflect hazards presented by this or any other material under actual fire conditions. A flame spread index of 75 or less meets code requirements regarding flame spread for foam plastic roof insulation. However, flame spread values are not required for foam plastic insulation used in roof deck constructions that comply as an assembly with FM 4450 or UL 1256.

#### Installation

Refer to the CertainTeed FlintBoard product brochure and to the CertainTeed Commercial Roof Systems Manual for installation details regarding FlintBoard Roof Insulation. Refer also to Technical Bulletin CT-ISO-08-02.

#### Storage

**Storage/Precautions:** Factory-applied packaging is intended only for protection during transit. When stored outdoors or on the job site, packages should be stacked on pallets at least three inches above ground level and completely covered with a weatherproof covering such as a tarpaulin. The temporary factory-applied packaging should be slit or removed to prevent accumulation of condensation. Roof insulation which has become wet or damaged should be removed and replaced with solid, dry insulation.

**Warning!** Do Not Leave Exposed: This product is a polyiso organic plastic foam and will burn if exposed to an ignition source of sufficient heat and intensity, or open flame, such as a welder's torch. Like other organic materials, this product will release smoke if ignited. Do not apply flame directly to FlintBoard roof insulations. This product should be used only in strict accordance with CertainTeed recommended uses and instructions.

**FlintBoard ISO-T Compliances:**

- ASTM C1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi)
- Miami-Dade County, Florida
- California State Insulation Quality Standards and Title 25, Foam Flammability Criteria
- IBC, BOCA, ICBO, and SBCCI Sections on Foam Insulation
- CCMC
- Meets CAN/CGSB-51.26-M86. Meets CAN/ULC-S770 and CAN/ULC-S704

**FM Standard 4450/4470 Approval**

FlintBoard ISO-T is approved for Class 1 insulated steel, wood, concrete and gypsum roof deck construction for both 1-60 and 1-90 Windstorm Classifications (may be mopped or mechanically fastened to concrete roof deck). Refer to FM Approval Guide for details on specific systems.

**UL Standard 1256 Classification**

Insulated metal deck construction assemblies, Construction #120 and #123.

**UL Standard 790 (ASTM E108) Classification**

Class A with most roof membrane systems. See UL Roofing Materials & Systems Directory.

**UL Standard 263 Fire Resistance Classification (ASTM E119)**

Some classifications for fire resistance are P225, P230, P259, P508, P510, P514, P701, P710, P713, P717, P718, P719, P720, P722, P723, P724, P725, P727, P728, P729, P730, P732, P801, P814, P815, P818, P819, and P828. See UL Fire Resistance Directory for updated listings.

**UL Certified for Canada**

**UL of Canada**

Insulated Roof Deck Assemblies  
Construction #C34

Meets CAN/ULC-S126-M86, CAN/ULC-S101-M89, and CAN/ULC-S107-M87 Criteria.

**FlintBoard ISO-T Thicknesses and LTTR**

Marking	Thickness		LTTR Value*	Slope	
	IN	MM		per ft	percent
AA	.05-1.0	12-25	4.2	1/8"	1%
A	1.0-1.5	25-38	7.0	1/8"	1%
B	1.5-2.0	38-50	9.9	1/8"	1%
C	2.0-2.5	50-63	12.9	1/8"	1%
X	.05-1.5	12-38	5.6	1/4"	2%
Y	1.5-2.5	38-63	11.4	1/4"	2%
Q	0.5-2.5	12-63	8.5	1/2"	4%

\*LTTR (Long-term thermal resistance) values are based on ASTM C 1289, effective 1/1/2014, which provides updated 15 year time weighted averages.

For more information, contact CertainTeed Commercial Roofing Technical Services at 800-396-8134 x2.

**ASK ABOUT ALL OF OUR OTHER CERTAINTEED® PRODUCTS AND SYSTEMS:**

ROOFING • SIDING • TRIM • DECKING • RAILING • FENCE  
GYPSUM • CEILINGS • INSULATION

[www.certainteed.com](http://www.certainteed.com) <http://blog.certainteed.com>

CertainTeed Corporation  
P.O. Box 860  
Valley Forge, PA 19482

Professional: 800-233-8990  
Consumer: 800-782-8777

